

PAT

Photographic Activity Test (Per ISO 18916) Research Report

Customer: Werner Markiewicz
Company: Neschen AG
Address: Hans-Neschen-Str.1
31675 Bückeberg
Germany

Date: 3/25/15
Job: 2265

Material: Filmoplast P 90

Silver Image Interaction

Density change of control: -1.29
Upper pass/fail limit: -1.03
Density change of material: -1.20
Lower pass/fail limit: -1.55

Density change caused by material must fall between upper and lower limits ($\pm 20\%$ change in control)

Material pass/fail: Pass
Reason: Within image interaction limits

* Control material in Whatman No. 1 filter paper

Andrea Venosa
Operator

Note: The PAT should always be used in conjunction with ISO 18902, *Imaging Materials - Processed Photographic Films, Plates, and Papers - Filing Enclosures and Storage Containers*, when selecting enclosures.

Gelatin Staining

Density change of control: 0.12
Stain limit: 0.20
Density change of material: 0.13

Staining caused by material must be less than stain limit (control +0.08)

Result: Pass
Reason: Less than stain limit

Mottling of Image Interaction Detector

Visual assessment of uniform action

Result: Pass

Overall Performance - Must pass all criteria: Pass

This certificate is valid for this specific lot of product until any date, or for any subsequent lot of this product produced until: **3/24/16**
This certificate is void upon any change in product formulation, or change in manufacturer or manufacturer suppliers.